



Flexitallic[®]

THERMICULITE[®]


Sealing materials for
Solid Oxide Fuel Cells.



THERMICULITE®



Crystal plates: Each crystal plate is nanometres thick



Structure of Thermiculite® 866

Proven sealing materials for Solid Oxide Fuel Cells.

Thermiculite®

THERMICULITE® 866

- Thermiculite® 866 is recognised as the material of choice to achieve high sealing efficiency by leading developers of SOFC technology
- Thermiculite® 866 ensures that a seal is created and then maintained in service
- No burn off of organic material at elevated temperature
- No reduction in gasket thickness at elevated temperature
- Sealing performance not reduced by thermal cycling

THERMICULITE® 870

- Sealing achieved at very low surface stresses
- Very high compressibility
- Sealing performance not reduced by thermal cycling
- Gasket cutting just as easy for Thermiculite® 866

Thermiculite® 866 and 870 are sealing materials specifically designed for use as compression seals for Solid Oxide Fuel Cells (SOFC) and Solid Oxide Electrolysers (SOE). They have been used very successfully in a range of SOFC applications around the world.

TH866 and TH870 utilise the unique properties of Thermiculite® technology, based upon the use of chemically exfoliated vermiculite, developed by Flexitallic to produce a range of high performance, high temperature resistant, patented sealing materials for industrial applications.

Vermiculite is a naturally occurring mineral noted for its high temperature capability, wide chemical resistance and electrical insulation properties. Vermiculite occurs naturally as flakes which consist of a stack of very many crystal plates where each crystal plate is nanometres thick. These flakes are able to be exfoliated so that the crystal plates separate from each other.

Partial exfoliation can be achieved by the application of heat, resulting in a coarse expanded form of vermiculite however the crystal layers can also be separated efficiently from each other by chemical means which produces a form which consists of just these very thin, high aspect ratio crystal plates. The separated plates are highly flexible and have the useful property of adhering to each other to produce a thin, flexible film. The self binding nature of the vermiculite means additional compounds can be added without the need for a supplementary binder.

By exploiting these properties, Flexitallic has developed a process to produce a very compressible, flexible sheet sealing material with very tightly controlled thickness and density. The resulting sheet material can be easily cut into gaskets with complex shapes including those with narrow land widths ($\geq 4\text{mm}$). The controllable manufacturing approach means sheet material can be produced in a range of thicknesses to suit different designs.

Thermiculite® ensures that a seal can be created and then maintained in service. Thermiculite® 866 is soft, resulting in a compressible and flexible material that is completely free of organic content.


Due to its unique chemical and physical properties, TH866 and TH870 are both highly temperature resistant (1000°C) and, as there is no organic content, there is no burn off of volatile components at SOFC operational temperatures. It also means that the sensitive cell chemistry is not poisoned.

At elevated temperature there is also no reduction in the gasket thickness and no resulting relaxation of the bolts. The seal is therefore stable during cycling between ambient and operational temperatures.

Thermiculite® 866 provides excellent service performance. Figures 3 and 4 show stack results obtained by a customer and reproduced with their full permission.

THERMICULITE® 866 and 870 THE PROVEN SEALING MATERIAL FOR SOFC APPLICATIONS

Stable to high temperatures up to 1000°C	No thermal degradation of the seal at SOFC operating temperatures	Extended lifetime performance
No organic filler material	Excellent seal integrity maintained	Material does not become porous over time or suffer a gasket thickness reduction
Soft and compressible	Easily cut into complex shapes and profiles	Complex sealing arrangements are easily accommodated
Currently operating in service units	Case studies providing the benefits of Thermiculite® 866	Many reports of very low leakage rates even through many thermal cycles



Advanced test equipment aided Flexitallic's development of Thermiculite® 866

For some SOFC designs a softer, more compressible sealing material is required. As a result of this requirement, Flexitallic developed Thermiculite® 870, building upon the knowledge and experience gained from TH866. TH870 is significantly more compressible under low loads, e.g. 1MPa. TH870 is around ten times more compressible than TH866.

Figure 1 shows load vs deflection for TH870 compared to TH866. At a stress of 1 MPa TH870 compresses 0.22mm whereas TH866 gasket only compresses 0.02mm under the same load.

Thermiculite® 870 also seals at a comparable level to TH866, but at much lower applied loads. This is the case at ambient and elevated temperatures. Figure 2 shows an 80 hour leakage test at ambient temperature.






For more information see Introduction of a *Low Sealing Stress Vermiculite Based Compression Gasket for SOFCs*; S Bond & S Shaw, ECS Trans. 2018 83(1): 159-170.

LS COATING

Thermiculite® 866 can be offered with an additional glass based surface coating. This material is known as **TH866LS**. A thin coating of glass powder is bound to each surface of the sheet during the manufacturing process so that at the operational temperature of the SOFC cell the coating melts therefore reducing the interfacial leakage paths.

No initial glass sintering cycle to above the operating temperature of the SOFC stack is required with Thermiculite® 866 LS. Provided the service temperature is at least 700°C the glass coating will form the required seal.

Please note 866LS has now been superseded by TH870 material.



UNITED KINGDOM

Flexitallic UK Ltd

Scandinavia Mill
Hunsworth Lane
Cleckheaton
West Yorkshire, BD19 4LN
UK
Tel. +44 1274 851273
Fax. +44 1274 300303
www.flexitallic.com

**Branches also in Aberdeen,
Middlesbrough, Ellesmere
Port and South West.**

BENELUX

Flexitallic Benelux BVBA

Smallandlaan 21
2660 Hoboken
BELGIUM
Tel. + 32 3 369 19 68
www.flexitallic.com

CHINA

Flexitallic Gasket Technology (Suzhou) Co., Ltd

Building A, 1868 Guangming Rd
Technological Development Zone
WuJiang Economic 215200
CHINA
Tel. +86 512 6303 2839
Fax. +86 512 6303 2879
www.flexitallic.com

UNITED STATES

Flexitallic US LLC

6915 Highway 225
Deer Park
Texas 77536
USA
Tel. +1 281 604 2400
Fax. +1 281 604 2415
www.flexitallic.com

FRANCE

Siem Supranite

a Flexitallic Company

31-33 Rue de Mogador
75009 Paris
FRANCE
Tel. +33 (0)1 48 88 88 88
Fax. +33 (0)1 47 66 88 44
www.siem.fr

ITALY

Flexitallic Italy Sr.l

Via Leonardo Da Vinci 6B
26020 Ticengo CR
ITALY
Tel. +39 0374 71006
Fax. +39 0374 71277
www.flexitallic.com

SINGAPORE

Flexitallic Ltd

Singapore Branch

Level 42 Suntec Tower Three
8 Temasek Boulevard
SINGAPORE
038988
Tel. +65 68663638
www.flexitallic.com

UNITED STATES

Custom Rubber Products

2625 Bennington
Houston
Texas 77093
USA
Tel. +1 713 691 2211
Fax. +1 713 691 3005
www.customrubber.com

GERMANY

Flexitallic GmbH

Halskestr. 4a
47877 Willich
GERMANY
Tel. +49 (0) 2154 95363-0
Fax. +49 (0) 2154 95363-29
www.flexitallic.com

UNITED ARAB EMIRATES

Flexitallic LLC

PO Box No. 6591-Al Jazeera
Plot 108, Road E, Al Hamra Industrial
Ras Al Khaimah
UNITED ARAB EMIRATES
Tel. +971 (0)7 243 4305
Fax. +971 (0)7 243 4306
www.flexitallic.com

THAILAND

Flexitallic Sealing Technology Co Ltd

No. 7/456, Moo 6,
Amata City Rayong Industrial Estate
Mabyangporn Sub-district
Pluak Daeng District
Rayong Province
THAILAND
Tel. +66 (0)33017561 ~ 3
Fax. +66 (0)33017564
www.flexitallic.com

CANADA

Flexitallic Canada Ltd

4340 - 78 Avenue
Edmonton
Alberta, T6B 3J5
CANADA
Tel. +780 466 5050
Fax. +780 465 1177
www.flexitallic.com

About The Flexitallic Group

The Flexitallic Group is a global leader in specialised sealing solutions and products serving the oil and gas, power generation, chemical and petrochemical industries in emerging and developed markets. Focused on the upstream, downstream and power generation sectors, it has operations in France, the United States, Canada, Mexico, the United Kingdom, Germany, Italy, Belgium, the United Arab Emirates, Thailand and China plus a network of worldwide licensing partners and distributors.

www.theflexitallicgroup.com